

Replacement Element Media

Cellulex™	
Appearance	White, corrugated
Use	Pleatable filter media
Composition	Cellulose fiber filter media
Area weight (DIN 53884)	108 g/m ²
Thickness (DIN 53885)	0,30 mm
Air Permeability (DIN53887)	460 m ³ /m ² .h at 200 Pa
Dimensional stability	N/A
Surface finish	N/A
Additional treatments	N/A
Surface electrical resistance (DIN 54345)	4,5 x 10 ⁹ Ohm
BIA Category (DIN 60335-2-69)	Class L Test report Nr. 200321240/6210
Temperature (dry heat)	
Continuous	65°C
Peaks	80°C
Chemical resistance	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising Agents	Poor
Organic Solvents	Fair
Abrasion Resistance	Good
Supports Combustion	Yes
Application field	Enhanced performance due to a unique combination of fiber sizes and a more uniform fiber distribution. Suited for applications with dry, coarse particulate. Cellulux media is superior to felts, fabrics, cotton cloths... Typical applications include metal working, shot blasting...

Replacement Element Media



www.donaldson.com

Humberstone Lane
Thurmaston
Leicester LE4 8HP
England

Tel +44 (0)116 269 6161
Fax +44 (0)116 269 3028

Email: IFS-uk@emea.donaldson.com

Research Park Zone 1
Interleuvenlaan 1
B-3001 Leuven (Heverlee)
Belgium

Tel +32 (0)16 383 970
Fax +32 (0)16 383 938

Email: IFS-europe@emea.donaldson.com